

# MARSCHALL LABORATORIES, INC.

2060 Palmetto St. • Clearwater, FL 33765 • Phone (727) 443-2771 • FAX (727) 443-2777

## Results

	ECO Satin Base White 11790	ECO Brilliant Base White 11930	
Lot No.	11790-3	11930-2	
Color	2048 White Café	Untinted	
Gloss - ASTM D523			
Gloss, 20 Degrees	6.7	51.5	
Gloss, 60 Degrees	42.1	83.9	
Gloss, 85 Degrees	91.9	104.0	
Block Resistance, ASTM D4946			
1 Day			
Room Temperature	9	9	
120°F	0	2	
7 Days			
Room Temperature	9	9	
120°F	8	8	
Scrub Resistance, ASTM D2486			
Cycles	332	649	
Yellowing Resistance			
Initial CIELAB Values			
L*	92.66	96.19	
a*	1.34	-0.92	
b*	8.52	3.62	
Chart Exposed to Ammonia (30 Minutes) (1)			
L*	92.54	95.90	
DL*	-0.12	-0.29	
a*	1.32	-1.06	
Da*	-0.02	-0.14	
b*	8.73	5.37	
Db*	0.21	1.75	Db* = 0 = No yellowing
DE	0.24	1.77	
Leveling			
Leneta, ASTM D4062	10	10	10 = Perfect flow & leveling rating



Daniel Marschall  
Marschall Labs Inc.  
December 21, 2017