

Technical Data Sheet

Hollandlac Brilliant 98

High performance, marine quality enamel, unequalled in its ability to provide maximum protection and depth of color. Interior or exterior, marine quality, oil based, ultra high-gloss enamel.

- Splendid high-gloss
- Long color durability
- Virtually non-yellowing
- Perfect coverage
- Excellent flow

PRODUCT

INTENDED USE	Exterior and interior, pre-treated wood, plaster, wallboard, metals and plastic. Can be applied over the existing paint after first thoroughly cleaning and sanding the surface. Refer to the Primers and Undercoats section of our website for the appropriate primer to use depending on the surface and type of existing paint.
SITUATION	Exterior/Interior
PACKAGING	1 l, 2.5 l
COLORS	All colors available via Fine Paints of Europe color mixing system
GLOSS LEVEL	High gloss, approx. 98 G.U. at 85 °
BINDER	Alkyd resins
PIGMENT	Titanium Dioxide, mineral and organic color pigments
SOLIDS CONTENT	Approx. 69 volume %
DENSITY AT 68 °F	Approx. 1,13 kg/dm ³
VISCOSITY AT 68 °F	Approx. 80 K.U.
DRYING TIME	Drying time (68 °F / 65 % R.H.): dust-free after approx.4-6 hr; recoatable after approx. 18 hr. Drying times are average values and provided as an indication only; actual drying time will depend on weather conditions, film thickness and choice of color. Darker colors, applied in lower temperatures will take longer to dry than whites and lighter colors.
ELASTICITY	7 mm Erichsen

NOTE: The properties and specifications can vary depending on the color. The values stated are typical.

APPLICATION

Technical Data Sheet

APPLICATION BY	Use a first quality, clean, natural bristle brush. We recommend the following brushes for this finish: Omega Small Flats (S57's), or Omega Round Sash (S203's). NEVER use a roller to apply this finish to high profile areas as a slight stipple will be evident.
DILUTION	Ready to use.
TOOLS/EQUIPMENT CLEANING	FPE Mineral Spirits.
APPLICATION TEMPERATURE / R.H.	Min. 45 °F - max. 77 °F ambient and substrate temp., relative humidity max. 85 %. Substrate temperature min. 38 °F above dew point.
THEORETICAL COVERAGE	covers approx 168 square feet per liter
FILM THICKNESS	30 microns dry film thickness (= approx. 60 microns wet film thickness) Check the dew point regularly when applying at low temperatures. With wood and metal substrates, this can have a major influence on the ability to apply the coating, as well as on the drying and gloss of the applied coating.

STORAGE AND USE PERIOD

STORAGE	Cool and above freezing point; do not allow product quality to deteriorate during storage.
USE WITHIN	12 Months (in unopened packaging) After opening the packaging, the effect of 'preservatives' in the paint may be reduced. In exceptional cases, this can give bacteria and molds free rein from outside, which could spoil the product.

The details in this product data sheet are correct at the time of printing. The information provided about this product is regularly updated, and amendments may therefore be made at any time without notice. Fine Paints of Europe expressly disclaims any and all liability related to damages resulting from errors or omissions in the information provided herein, except in the event of malicious intent or gross negligence.