

Technical Data Sheet

Oil Primer/Undercoat

Oil Primer/Undercoat is a high-build primer for exterior or interior use – may remain unpainted for up to twelve months, before painting. Sophisticated, understated sheen

- Conceals minor surface flaws
- Virtually non-yellowing
- Perfect coverage
- Excellent flow

PRODUCT

| | |
|--------------------|---|
| INTENDED USE | Interior and exterior untreated wood, plaster, wallboard. This primer is an ideal foundation for the HOLLANDLAC, ECO and Eurolux House Paint systems. |
| SITUATION | Exterior/Interior |
| PACKAGING | 1 l, 2.5 l |
| COLORS | All colors available via Fine Paints of Europe color mixing system |
| GLOSS LEVEL | Satin, approx. 35 G.U. at 60 ° |
| BINDER | Alkyd resins |
| PIGMENT | Titanium Dioxide, mineral and organic color pigments |
| SOLIDS CONTENT | Approx. 60 volume % |
| DENSITY AT 68 °F | Approx. 1,15 kg/dm ³ |
| VISCOSITY AT 68 °F | Approx. 90 K.U. |
| DRYING TIME | Drying time (68 °F / 65 % R.H.): dust-free after approx.3 hr; recoatable after approx. 18 hr. Drying times are average values and provided as an indication only; actual drying time will depend on weather conditions, film thickness and choice of color. Darker colors, applied in lower temperatures will take longer to dry than whites and lighter colors. |
| ELASTICITY | 7 mm Erichsen |

NOTE: The properties and specifications can vary depending on the color. The values stated are typical.

APPLICATION

Technical Data Sheet

| | |
|--------------------------------|---|
| APPLICATION BY | Use a first quality, clean, natural bristle brush. We recommend the following brushes for this finish: Omega Small Flats (S57's) or Omega Round Sash (S203's) or premium quality professional roller covers in 3/8" nap. |
| DILUTION | Ready to use. |
| TOOLS/EQUIPMENT CLEANING | FPE Mineral Spirits. |
| APPLICATION TEMPERATURE / R.H. | Min. 45 °F - max. 77 °F ambient and substrate temp., relative humidity max. 85 %. Substrate temperature min. 38 °F above dew point. |
| THEORETICAL COVERAGE | covers approx 144 square feet per liter |
| FILM THICKNESS | 33 microns dry film thickness (= approx. 65 microns wet film thickness) Check the dew point regularly when applying at low temperatures. With wood and metal substrates, this can have a major influence on the ability to apply the coating, as well as on the drying and gloss of the applied coating. |

STORAGE AND USE PERIOD

| | |
|------------|--|
| STORAGE | Cool and above freezing point; do not allow product quality to deteriorate during storage. |
| USE WITHIN | 12 Months (in unopened packaging) After opening the packaging, the effect of 'preservatives' in the paint may be reduced. In exceptional cases, this can give bacteria and molds free rein from outside, which could spoil the product. |

The details in this product data sheet are correct at the time of printing. The information provided about this product is regularly updated, and amendments may therefore be made at any time without notice. Fine Paints of Europe expressly disclaims any and all liability related to damages resulting from errors or omissions in the information provided herein, except in the event of malicious intent or gross negligence.